



Product Data Sheet

Select Cast Machine Stretch Film



Effective 01/2017

Item ID Numbers:

CMF2065B, CMF2075A, CMF2075B, CMF2090A, CMF2011A, CMF2011B, CMF2011C, CMF2012A, CMF20135B, CMF2015A, CMF3075A, CMF3075B, CMF3090A, CMF3011B, CMF3012A, CMF3012B, CMF3015A, CMF1012A, CMF1012B, CMF1090A, CMF10150A, CMF12150A, CMF1290A, CMF1512B

Nominal Values:

Film Properties	ASTM Test Method	65 Gauge	75 Gauge	90 Gauge	115 Gauge	120 Gauge	135 Gauge	150 Gauge
Tensile @ Break MD (psi)	D-882	6,000	6,800	6,200	6,200	6,000	6900	6500
Tensile @ Break TD (psi)	D-882	4,100	4200	4,100	4,000	4,100	4700	4100
Tensile @ Yield MD (psi)	D-882	1,250	1,250	1,330	1,400	1,500	1250	1300
Tensile @ Yield TD (psi)	D-882	1,100	1,100	1,150	1,250	1,300	1100	1200
Elongation MD (%)	D-882	580	650	500	525	550	850	660
Elongation TD (%)	D-882	820	780	610	600	675	950	880
Elmendorf Tear MD (g/mil)	D-1922	330	325	500	325	300	330	230
Elmendorf Tear TD (g/mil)	D-1922	650	640	900	535	530	640	620

Wrap Tite, Inc.

6200 Cochran Rd.

Solon, Ohio 44139

Toll Free: 888-WRAP TITE (972-7848)

Fax: 440-349-5432

www.wraptite.com – info@wraptite.com



NOTE: MD = Machine Direction

TD = Transverse Direction